

Galvanized steel wire COIL

- Galvanised steel wire
- Rosette weight from 1000 kg to 2300 kg fitted with 4 metal straps
- Wire diameter from 3.20 mm until 8.30 mm
- Unwinding anticlockwise



Coil dimensions

Ø Wire (mm)	Weight (kg)	Ø Interior (mm)	Ø Exterior (mm)	h (mm)
3,20 – 6,30	1000 – 1500	580 – 620	800 – 1100	600 ó 750

Specifications by diameter

Diameter (mm)	Diameter Tolerance (mm)	Ovality (max./mm)	Tensile strength (MPa)	Min. Elongation min. Agt (%)	Galvanizing 99,995% zinc (EN 10244-2, Class D)
3,20	± 0,05	0,10	750-900	1,0	≥ 40 gr/m ²
3,40	± 0,05	0,10	750-900	1,0	≥ 40 gr/m ²
3,75	± 0,06	0,10	750-900	1,0	≥ 40 gr/m ²
4,00	± 0,06	0,10	700-850	1,0	≥ 40 gr/m ²
4,30	± 0,06	0,10	600-800	1,5	≥ 40 gr/m ²
4,50	± 0,06	0,10	600-800	1,5	≥ 40 gr/m ²
4,65	± 0,06	0,10	600-800	1,5	≥ 40 gr/m ²
5,00	± 0,07	0,10	600-800	1,5	≥ 40 gr/m ²
5,50	± 0,07	0,10	550-750	1,5	≥ 40 gr/m ²
5,55	± 0,07	0,10	550-750	1,5	≥ 40 gr/m ²
6,30	± 0,07	0,10	550-750	1,5	≥ 40 gr/m ²
7,50	± 0,08	0,10	550-750	1,5	≥ 40 gr/m ²
7,55	± 0,08	0,10	550-750	1,5	≥ 40 gr/m ²
8,30	± 0,08	0,10	550-750	1,5	≥ 40 gr/m ²



Exel Fil, S.A.
Apdo. de Correos 129
Polígono Industrial s/n
25200 Cervera (Spain)
Tel. + (34) 97 353 22 12
Fax + (34) 97 353 28 09
exelfil@exelfil.com
www.exelfil.com

Sales office / Export
Ganduxer, 127 bajos
08022 Barcelona (Spain)
Tel. + (34) 93 253 17 22
Fax + (34) 93 253 05 83
export@exelfil.com
www.exelfil.com